





12030CASALGRASSO-CN-ITALY
funiflex.sollevamenti@gmail.com

FUNIFLEX SOLLEVAMENTI SRL



SPELTER SOCKETS /TIRANTI TESTE FUSE CON RESINA

safety factor de 3 a 5:1
EN 13411



Ø FUNE	RESISTENZA				TIPO	PEAR					
	1770	1960	2160	SPIROID.		Ø FUNE	A	B	D	C	E
mm	kN	kN	kN	kN	mm	mm	mm	mm	mm	mm	mm
10	75.4	84.4	96.3	109	11	20.6	45	20.6	17.5	24	52
12	100.5	122	139	152	13	15	45	25.4	23	30	59
14	149	165	191	202	15	32	63	30	26	36	65
16	195	216	249			32	63	30	25	36	65
18	242.8	273	316	322	19	38	76	35	32	42	78
20	306	338	390			45	89	41	38	50	90
22	370	408	471	430	22	45	89	41	38	50	90
24	440.6	486	561	512	24	51	101	51	45	57	103
26	472	571	654	601	26	51	101	51	45	57	103
28	547	662	759	697	28	57	114	57	51	65	116
30	628	760	871	799	30	57	114	57	51	65	116
32	715	864	991	909	32	63	127	63	57	71	130
34	807	954	1120	1030	34	63	127	63	57	71	130
36	904	1070	1250	1150	36	63	127	63	57	80	155
38	1007	1190	1400	1280	38	76	162	70	63	80	155
40	1120	1320	1550	1420	40	76	165	76	70	84	171
44	1350	1570	1940	1720	44	89	178	89	76	95	198
48	1610	1870	2300	2040	48	89	178	89	76	95	198
50	1745	2030	2500	2220	50	101	228	95	82	96	224
52	1890	2190	2700	2590	54	101	228	95	83	111	224
60				3210	60	113	254	108	92	125	248
66				3780	66	127	273	121	102	140	270